

This item is the archived peer-reviewed author-version of:

Peculiar piezoelectric properties of soft two-dimensional materials

Reference:

Sevik Cem, Çakir Deniz, Gulseren Oguz, Peeters François.- Peculiar piezoelectric properties of soft two-dimensional materials The journal of physical chemistry : C : nanomaterials and interfaces - ISSN 1932-7447 - 120:26(2016), p. 13948-13953 Full text (Publisher's DOI): http://dx.doi.org/doi:10.1021/ACS.JPCC.6B03543 To cite this reference: http://hdl.handle.net/10067/1349480151162165141

uantwerpen.be

Institutional repository IRUA

THE JOURNAL OF PHYSICAL CHEMISTRY

Subscriber access provided by UNIV OF NEBRASKA - LINCOLN

Peculiar Piezoelectric Properties of Soft Two-Dimensional Materials

Cem Sevik, Deniz Cakir, Oguz Gulseren, and Francois M. Peeters

J. Phys. Chem. C, Just Accepted Manuscript • DOI: 10.1021/acs.jpcc.6b03543 • Publication Date (Web): 09 Jun 2016 Downloaded from http://pubs.acs.org on June 13, 2016

Just Accepted

Article

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a free service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are accessible to all readers and citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.



The Journal of Physical Chemistry C is published by the American Chemical Society. 1155 Sixteenth Street N.W., Washington, DC 20036

Published by American Chemical Society. Copyright © American Chemical Society. However, no copyright claim is made to original U.S. Government works, or works produced by employees of any Commonwealth realm Crown government in the course of their duties.

4 5

6 7 8

9 10 11

12

13

14 15

16

17 18

19

20

25 26 27

28

29

30

31 32

33

34

35

36

37

38

39

40

41 42

43

44

45

46

47 48

49

50

51

52 53

54

55

56

57

58 59

60

Peculiar Piezoelectric Properties of Soft Two-Dimensional Materials

Cem Sevik,*,[†] Deniz Çakır,*,[‡] Oğuz Gülseren,*,[¶] and François M. Peeters*,[‡]

[†]Department of Mechanical Engineering, Faculty of Engineering, Anadolu University, Eskisehir, TR 26555, Turkey.

[‡]Department of Physics, University of Antwerp, Groenenborgerlaan 171, B-2020, Antwerpen, Belgium.

¶Department of Physics, Bilkent University, Bilkent, Ankara 06800, Turkey.

E-mail: csevik@anadolu.edu.tr; deniz.cakir@uantwerpen.be; gulseren@fen.bilkent.edu.tr; francois.peeters@uantwerpen.be Phone: +9 (0)532 1673208

Abstract

II-VI semiconductor honeycomb monolayers have a non-centrosymmetric crystal structure and therefore are expected to be important for nano piezoelectric device applications. This motivated us to perform first-principles calculations based on density functional theory to unveil the piezoelectric properties (i.e. piezoelectric stress (e_{11}) and piezoelectric strain (d_{11}) coefficients) of these monolayer materials with chemical formula MX (where M = Be, Mg, Ca, Sr, Ba, Zr, Cd and X=S, Se, Te). We found that these two-dimensional materials have peculiar piezoelectric properties with d_{11} coefficients one order of magnitude larger than those of commercially utilized bulk materials. A clear trend in their piezoelectric properties emerges, which originates mainly from their mechanical properties. We establish a simple correlation between the piezoelectric strain coefficients and the physical properties, as the natural elemental polarizabilities, the Bader charges and lattice constants of the individual M/X atoms and MX monolayers.

Introduction

Recent experimental and theoretical studies revealed that non-centrosymmetric twodimensional (2D) materials exhibit high piezoelectric responses which makes them very appealing for next generation of sensors, actuators, transducers, and energy harvesters. Those applications are in the fields of nanorobotics, piezotronics, and nanoelectromechanical systems.^{1–8} The piezoelectric properties of single layer BN, MoS₂, MoSe₂, MoTe₂, WS₂, WSe₂, and WTe_2 were previously studied⁹⁻¹² and it was reported that the relaxed-ion piezoelectric stress (e_{11}) and piezoelectric strain (d_{11}) coefficients of these monolayers are comparable or even better than those of conventional bulk piezoelectric materials. Likewise, Zhuang et al.¹³ have shown that both the e_{11} and d_{11} coefficients of CrS_2 are significantly larger than those of single layer MoS_2 . Subsequently, Wu et al.¹ reported experimental evidence of piezoelectricity in free-standing monolayer MoS_2 and they found that this material exhibits a strong piezoelectric effect for an odd number of layers in which case inversion symmetry is broken. Moreover, Zhu *et al.*² measured the e_{11} coefficient of this monolayer material and found 2.9×10^{-10} Cm⁻¹, which is in good agreement

60

with previous theoretical calculation.⁹

Following these studies, the piezoelectric properties of different non-centrosymetric 2D monolayer materials such as transition metal dichalcogenides (TMDCs) and oxides,^{14,15} group III monochalcogenides,¹⁶ and group IV monochalcogenides 3,17 were studied by first principles calculations. Rather surprisingly, the relaxed ion d_{11} coefficient, which is a measure of the mechanical-electrical energy conversion ratio, of some of these materials were predicted to be one or two orders of magnitude larger than that of traditionally used bulk materials such as α -quartz¹⁸ (d_{11} =2.3 pmV⁻¹), wurtzite- GaN^{19} $(d_{33}=3.1 \text{ pmV}^{-1})$, and wurtzite-AlN¹⁹ $(d_{33}=5.1 \text{ pmV}^{-1})$. For instance, values as high as 8.47, 16.3, 21.7, 212.1, and 250.5 pmV^{-1} have been obtained for monolayer CrSe₂, CrTe₂,¹⁴ CdO,¹⁵ GeSe, and SnSe³ crystals, respectively. These results clearly show the remarkably high piezoelectric properties of monolayer materials and their potential use for nanoscale technological applications.



Figure 1: Top and side views of graphene-like honeycomb structure for group II-VI MX monolayers, where M= Be, Mg, Ca, Sr, Ba, Zr, Cd and X=S, Se, Te. Δ_B is the buckling parameter for the non-planar monolayers.

Recently, Zheng $et \ al.^{20}$ explored the structural stability of two dimensional II-VI hon-

eycomb structures using first principles latticevibration frequency analysis and reported that graphenelike monolayers of BeO, MgO, CaO, ZnO, CdO, CaS, SrS, SrSe, BaTe, and HgTe are dynamically stable. In addition, they confirmed the intrinsic semiconductor nature of these materials by hybrid functional calculations. These results motivated us to perform a systematic first principles study to investigate piezoelectric and mechanical properties of these non-centrosymmetric single layer materials with chemical formula MX, where M = Be, Mg, Ca, Sr, Ba, Zn, Cd and X=S, Se, Te. Lattice parameters, elastic stiffness constants $(C_{11} \text{ and } C_{12})$, Young modulus (Y), piezoelectric stress coefficients (e_{11}) and piezoelectric strain coefficients (d_{11}) are calculated.

The present paper is organized as follows. We first present our computational methodology. Then, we calculated the elastic constants and piezoelectric properties. Lastly, we conclude with an overview of our main results.

Method

Within the scope of the current study, first-principles calculations based on density functional-theory (DFT), as implemented in the Vienna Ab initio Simulation package (VASP) code, 21,22 are performed. The exchange-correlation interactions are treated using the generalized gradient approximation (GGA) within the Perdew-Burke-Ernzerhof (PBE) formulation 23,24 . The single electron wave functions are expanded in plane waves with kinetic energy cutoff of 600 eV. For the structure optimizations, the Brillouin-zone integrations are performed using a Γ -centered regular $26 \times 26 \times 1$ k-point mesh within the Monkhorst-Pack scheme.²⁵ The convergence criterion for electronic and ionic relaxations are set as 10^{-7} and 10^{-3} eV/Å, respectively. In order to minimize the periodic interaction along the z-direction the vacuum space between the layers is taken at least 15 Å. The coefficients of elastic stiffness tensor and piezoelectric tensor, e_{ijk} are obtained by using density-functional perturbation theory $(DFPT)^{26}$ as implemented

2

3 4

5

6

7 8

9

10

11

12

13 14

15

16

17

18 19

20

21

22

23

24

25

26

27

28

29

30

31

32

33

34 35

36

37

38

39 40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55 56

57

58

59

60

in the VASP code. Here, a highly dense k-point mesh, $36 \times 36 \times 1$, is used to accurately predict these tensor components. The clamped-ion elastic and piezoelectric coefficients are obtained from the purely electronic contribution and the relaxed-ion coefficients are obtained from the sum of ionic and electronic contributions.

The number of independent piezoelectric tensor coefficient is deduced from the symmetry of the crystal and thus the piezoelectric tensor of these hexagonal crystal systems, schematically shown in Figure 1 becomes:

$$e_{ij} = \begin{pmatrix} e_{11} & -e_{11} & 0\\ 0 & 0 & -\frac{e_{11}}{2}\\ e_{31} & e_{31} & 0 \end{pmatrix}.$$
 (1)

Here, we only need to calculate the e_{11} component of the piezoelectric stress tensor. The piezoelectric coefficient e_{31} is only relevant for a buckled monolayer. Since the calculated e_{31} and d_{31} coefficients are quite small, we are only interested in the in-plane piezoelectric properties. Following the e_{11} calculations, the corresponding piezoelectric strain tensor (d_{11}) of each material is predicted from the following relation as previously shown by Duerloo *et al.*⁹

$$d_{11} = e_{11} / (C_{11} - C_{12}).$$
 (2)

Results

It is essential that a piezoelectric material has to be an insulator or semiconductor with a sufficiently wide band gap to avoid current leakage. Zheng *et al.*²⁰ confirmed the intrinsic semiconductor nature of the materials considered in this study by hybrid functional calculations. They estimated indirect band gap values of MX with M= Be, Mg, Ca, Sr, Ba and direct band gap values of MX with M= Zn and Cd as large as 2 eV which are sufficiently large for piezoelectric applications.

With the intention to investigate piezoelectric properties of these materials, we first optimize the geometries and calculate the relaxed- and clamped-ion elastic stiffness coefficients (C_{11} and C_{12}), Young's modulus (Y =

 $(\mathrm{C}_{11}^2$ - $\mathrm{C}_{12}^2)/\mathrm{C}_{11}),$ and the Poisson's ratios (ν $=C_{12}/C_{11}$) of all the materials as depicted in Table 1. Since local density approximation was used in Ref. 20, we obtain slightly larger equilibrium lattice constants. The calculated buckling parameters, Δ_B (see Figure 1), for nonplanar structures are 0.21, 0.41, 0.32, and 0.49A for ZnSe, ZnTe, CdSe, and CdTe, respectively. The first observation from Table 1 is that C_{11} , C_{12} , Y, and ν of group II-VI materials decreases with increase in the row number of the group II element. In addition, for each group II element, the MX monolayer becomes stiffer with increase in the row number of the group VI element. Note that the relaxed-ion elastic constants, *i.e.*, C_{11} and C_{12} , are mostly smaller than the clamped-ion ones since the internal relaxation of the ions allows to release some of the stress in the former, see Table 1. All the materials considered in this study are found to be less stiff when compared to graphene (Y = 341 N/m,²⁷ single layer *h*-BN (Y = 275.9) N/m,²⁷ and most of the TMDCs¹⁴ and the Poisson ratio, ν of most of the MX compounds are much larger than that of TMDCs.²⁷ On the other hand, it should be noticed that the calculated elastic constants are positive and satisfy the Born stability criteria for crystals having hexagonal symmetry (for which, following conditions must be met for mechanically stable hexagonal crystals: $C_{11} > |C_{12}|$ and $C_{11} > 0$).^{28,29}

Figure 2 shows the results for clamped-(purely electronic) and relaxed-ion (electronic plus ionic) e_{11} and d_{11} coefficients of MX structures with M=Be, Mg, Ca, Sr, Ba and X=S, Se, Te. The calculated values clearly show that the electronic and ionic polarization of these materials have opposite sign and the magnitude of the ionic contribution is larger than the electronic contribution for all the considered materials except those with Be atom.

The contribution of the internal relaxation to the relaxed-ion e_{11} coefficients decreases when moving downward in the group of chalcogenide atoms. Owing to their larger in-plane lattice parameters, the MX compounds with larger M and X atoms undergo a smaller internal relaxation, which reduces the ionic contribution. This may be due to the fact that

ACS Paragon Plus Environment

Table 1: Calculated equilibrium lattice constants a_0 (in units of Å), net Bader charge Q on the metal atoms (in units of e^-), electronegativity difference ($\Delta \chi = \chi_X - \chi_M$) of M and X atoms (in Pauling scale), clamped and relaxed-ion elastic constants C_{11} and C_{12} (in units of N/m), the Young modulus Y (in units of N/m), and the Poisson ratios ν (= C_{12}/C_{11}).

					Clan	nped			Rela	axed	
Material	a_0	Q	$\Delta \chi$	C_{11}	C_{12}	Y	ν	C_{11}	C_{12}	Y	ν
BeS	3.456	1.59	1.01	87	22	81	0.25	78	31	65	0.40
BeSe	3.671	1.55	0.98	75	19	70	0.25	67	26	57	0.39
BeTe	4.033	1.45	0.53	61	14	57	0.23	54	21	46	0.39
MgS	4.095	1.68	1.27	56	18	49	0.32	45	29	26	0.64
MgSe	4.308	1.60	1.24	48	16	42	0.33	39	25	23	0.64
MgTe	4.684	1.54	0.79	38	13	34	0.34	31	20	19	0.65
CaS	4.572	1.45	1.58	39	18	32	0.46	32	25	12	0.78
CaSe	4.780	1.44	1.55	35	15	28	0.43	27	22	9	0.81
CaTe	5.160	1.43	1.10	29	12	23	0.41	22	19	7	0.86
SrS	4.849	1.50	1.63	35	16	28	0.46	28	23	10	0.82
SrSe	5.058	1.48	1.60	31	14	25	0.45	24	20	8	0.83
SrTe	5.438	1.43	1.15	26	11	21	0.42	20	17	6	0.85
BaS	5.140	1.42	1.69	30	16	22	0.53	25	21	8	0.84
BaSe	5.350	1.39	1.66	27	14	20	0.52	22	18	7	0.82
BaTe	5.728	1.36	1.21	23	11	17	0.48	18	16	5	0.89
ZnS	3.892	0.95	0.93	70	19	64	0.27	59	30	44	0.51
ZnSe	4.097	0.74	0.90	58	16	54	0.28	40	15	34	0.38
ZnTe	4.404	0.50	0.45	47	13	43	0.28	34	13	29	0.38
CdS	4.258	0.90	0.89	56	18	50	0.32	46	28	28	0.61
CdSe	4.440	0.73	0.86	47	15	42	0.32	30	15	23	0.50
CdTe	4.723	0.52	0.41	39	12	35	0.31	25	11	20	0.44

MX compounds possessing large cell parameters have a very smooth potential energy surface. Thus moving slightly away from the equilibrium structure does not change the total energy of the system. While the clamped-ion e_{11} coefficients in the Ba-based compounds are larger than that in most of the group II elements, the relaxed-ion e_{11} coefficients exhibit a opposite behavior.

Among MX materials, MgS, CaS and CaSe have the highest and BeS has the smallest relaxed-ion e_{11} coefficients, as seen in Figure 2(a). Moreover, the predicted highest e_{11} coefficient is smaller than the one calculated for WS₂ (3.76,¹⁴ 2.47,⁹ and 2.12¹⁵) which has the smallest relaxed-ion coefficient among the Cr, Mo, and W based transition metal dichalcogenides (TMDCs). However, the picture is completely different when we consider the relaxedion d_{11} coefficient which is a measure of the mechanical-electrical energy conversion ratio, see Figure 2(b). In particular, the ones calculated for MX with M=Ca, Sr, and Ba are notably larger than the values predicted for TMDCs,^{9,14,15} most of the mono-layer materials such as BN, GaSe, GaAs, AlSb,^{3,20} and the bulk materials including α -quartz, wurtzite-GaN, and wurtzite-AlN^{18,19} which are widely used in industry. Furthermore, the materials previously reported as having good dynamic stability, namely CaS, SrS, SrSe, and BaTe,²⁰ have appreciable d_{11} coefficients with values of 18.66, 15.64, 18.73, and 19.92 pmV^{-1} , respectively.

As clearly understood from Eq. (2), such a remarkable d_{11} coefficient is obviously corre-

2

3

4

5

6

7

8

9

10

11

12

13

14

15

16

17

18

19

20

21

22

23

24

25 26

27

28

29

30

31 32

33 34

35

36

37

38

39

40

41

42

43

44

45

46

47

48

49

50

51

52

53

54

55

56

57

58

59

60



Figure 2: Calculated clamped and relaxed-ion (a) piezoelectric stress (e_{11}) and (b) piezoelectric strain (d_{11}) coefficients for MX monolayers (where M= Be, Mg, Ca, Sr and Ba). Red (gray) bars depict the relaxed-ion (clamped-ion) piezoelectric coefficients. For comparison, d_{11} coefficient of α -quartz, GaN and AlN are also depicted in (b). The white asterisk indicates that it is a dynamically stable material.

lated to the mechanical properties of the structures since these materials possess quite similar e_{11} coefficients, see elastic stiffness coefficients and Young's modulus listed in Table 1. This explicitly indicates that, in this material class, the remarkable piezoelectric potential originates mainly from their mechanical responses. While the relaxed-ion e_{11} coefficients of MX materials span a limited range (0.07-1.24 pC/m), the absolute values of the relaxed-ion d_{11} coefficient vary over a much larger range of 0.15-27 pm/V.

While the relaxed-ion e_{11} coefficient decreases when going from S to Te for all group II elements, the relaxed-ion d_{11} coefficient follows a different trend such that it increases when moving downward in the group of chalcogenides for the Ca, Sr and Ba atoms. BeX and MgX compounds have relatively large electronegativity difference, which is expected to result in large relaxed-ion d_{11} coefficients. However, due to their larger stiffness, the relaxed-ion d_{11} coefficients of the BeX and MgX compounds are found to be significantly smaller than that of MX with M=Ca, Sr and Ba but are comparable with those of commercial piezoelectric materials, see Figure 2(b). Here it should be mentioned that, among TMDCs with M=Cr, Mo and W, CrTe₂ has the largest d_{11} coefficient whereas BeTe has one of the smallest d_{11} coefficient among MX materials considered in this work.



Figure 3: Calculated clamped and relaxed-ion (a) piezoelectric stress (e_{11}) and (b) piezoelectric strain (d_{11}) coefficients for the MX monolayers (where M= Zr and Cd). Red (gray) bars depict the relaxed-ion (clamped-ion) piezoelectric coefficients.

In addition to Be, Mg, Ca, Sr, and Ba we also considered Zn and Cd based structures as well. Figure 3 shows the calculated e_{11} and d_{11} coefficients for ZnX, and CdX with X = S, Se, and Te. The relaxed-ion e_{11} coefficients of the MX materials (with M=Zn and Cd) fall into the range of 0.07-0.94 pC/m that are comparable with those of the MX materials (with M=Be, Mg, Ca, Sr and Ba), but are much smaller than the e_{11} coefficients of TMDCs. Furthermore, the clamped-ion e_{11} coefficients are quite similar for the ZnX and CdX compounds. This means that the ionic contribution determines the trends found for the relaxed-ion e_{11} coefficients, see Figure 3(a). Since the MX compounds are remarkably less stiff as compared to TMDCs, the predicted d_{11} coefficients of MX materials are comparable with that of TMDCs. In contrast to CaX, SrX and BaX, the relaxedion d_{11} coefficients of ZnX and CdX decrease when moving from S to Te. Similar trends also

ACS Paragon Plus Environment

have much larger d_{11} coefficients with respect to ZnX. Considering electronegativity differences between Zn/Cd and X atoms (which can be used to determine bond type in a material), the ZnX/CdX compounds with X=Te (S) belongs to a nonpolar covalent (polar covalent) bond class rather than a polar covalent (nonpolar covalent) bond class, which can be understood by comparing their Bader charges and electronegativity differences given in Table 1. Thus we can claim that the larger the electronegativity difference, the larger the d_{11} coefficient is. If one compares elastic constants, ZnX and CdX compounds are stiffer than the group II monochalcogenides. According to Eq. (2), the d_{11} coefficient is inversely proportional to (C₁₁- C_{12}) which is found to be large for ZnX and CdX materials. Even though Te is the most easily polarizable atom among the group VI elements, the relaxed-ion d_{11} coefficients of ZnTe and CdTe are found to be one third of those of ZnS and CdS.



Figure 4: Correlation between the relaxed-ion d_{11} coefficients of materials predicted by DFT calculations and the simple formula shown as inset. Here, α_{II} and α_{VI} represent the atomic polarizabilities³⁰ of the group II and VI atoms and c_1 and c_2 are constants. The red filled circles, brown filled squares, and green filled diamonds denote the MX monolayers with M= Be-Mg, Ca-Sr-Ba, and Zr-Cd groups, respectively.

erties of the MX materials are much more complicated. In the former, d_{11} is only governed by the ratio of the natural elemental polarizabilities of metal and chalcogenide atoms such that the d_{11} coefficient is maximized if we use a smaller metal atom and a larger chalcogenide atom.¹⁴ Finally, we attempt to relate the observed trends in the d_{11} coefficients to some physical properties, such as atomic polarizabilities, Bader charges, lattice constants etc., of individual atoms and their monolayers. We predict that the d_{11} coefficient of the materials under study are directly proportional to the ratio of natural elemental polarizabilities of M and X atoms and the product of lattice constants and Bader charges, as shown in Figure 4. There is a very good correlation between the coefficients calculated with the simple formula, $d_{11} = c_1 \frac{\alpha_{II}}{\alpha_{VI}} + c_2 a_0 Q_B$ and the DFPT calculations.¹⁵ Here, the natural elemental polarizabilities are borrowed from the experimental and calculated static dipole polarizabilities for the electronic ground states of neutral elements.³⁰ a_0 is the lattice constant and Q_B is the Bader charges given for the metal atoms (i.e Be, Mg, Ca, Sr, Ba, Zr, Cd) in Table 1. c_1 and c_2 are fitting constants shown in Table 2. In this equation, the second term is a kind of dipole moment scaled with a constant (i.e. c_2). Due to differences in mechanical properties of MX monolayers and electronic properties of individual M and X atoms, we identify three sets of fitting parameters that are exactly the same within the groups of Be-Mg, Ca-Sr-Ba, and Zn-Cd. In each fitting group, c_1 and c_2 parameters have opposite sign. According to this simple formula, there is a correlation between the d_{11} coefficient and the Bader charges. This simple expression also indicates that the d_{11} coefficient is maximized if one considers a smaller metal atom and a larger chalcogenide atom as we show for Ca, Sr and Be.

Conclusion

We presented a detailed theoretical investigation of the piezoelectric properties of semiconducting two-dimensional MX (where M= Be,

Compared to TMDCs, the piezoelectric prop-

ACS Paragon Plus Environment

2

3 4

5 6 7

8 9

10

11 12

13

14

15

16 17

18

19

20

21

22

23

24

25

26

27

28

29

30

31 32

33

34

35

36

37

38

39

40

41

42

43

44

45 46

47

48

49

50

51

52

53

54

55

56

57

58

59

60

Table 2: The correlation coefficients for the simple formula, $d_{11} = c_1 \frac{\alpha_{II}}{\alpha_{VI}} + c_2 a_0 Q_B$. Here, X represents S, Se, and Te atoms.

Materials	c_1	c_2
BeX, MgX	3.2295	-0.5501
CaX, SrX, BaX	-1.4305	4.1700
ZnX, CdX	9.6994	-4.4837

Mg, Ca, Sr, Ba, Zr, Cd and X=S, Se, Te) monolayers. These structures are found to be strong candidates for future atomically thin piezoelectric applications. Due to their mechanical softness, MX monolayers have a surprisingly very high relaxed-ion d_{11} coefficient. We showed that most of these materials have much better piezoelectric properties as compared to most of the other two-dimensional materials and the wellknown conventional bulk piezoelectric materials. Notable MX monolayers with good stability and high relaxed-ion d_{11} coefficient include BaTe (19.92 pm/V), SrSe (18.73 pm/V), SrS (15.64 pm/V) and CaS (18.66 pm/V). In addition, we noticed that it is possible to relate the calculated relaxed-ion d_{11} coefficients with atomic polarizabilities and the Bader charges of M and X atoms, and the structural properties of MX monolayers. The calculated relaxed-ion d_{11} coefficients can be fitted to a linear combination of two terms, the ratio of the M and X polarizabilities and the product of the Bader charges and in-plane lattice constants.

Acknowledgement This work was supported by the Flemish Science Foundation (FWO-VI), the Methusalem foundation of the Flemish government and the Bilateral program FWO-TUBITAK between Flanders and Turkey. We acknowledge the support from Scientific and Technological Research Council of Turkey (TUBITAK-115F024). Computational resources were provided by TUBITAK ULAK-BIM, High Performance and Grid Computing Center (TR-Grid e-Infrastructure), and HPC infrastructure of the University of Antwerp (Cal-cUA) a division of the Flemish Supercomputer Center (VSC), which is funded by the Hercules foundation. CS acknowledges the support from Scientific and Technological Research

Council of Turkey (TUBITAK-113F333) and the support from Anadolu University (BAP-1407F335, -1505F200), and Turkish Academy of Sciences (TUBA-GEBIP).

References

- Wu, W.; Wang, L.; Li, Y.; Zhang, F.; Lin, L.; Niu, S.; Chenet, D.; Zhang, X.; Hao, Y.; Heinz, T. F. et al. Piezoelectricity of Single-Atomic-Layer MoS₂ for Energy Conversion and Piezotronics. *Nature* **2014**, *514*, 470–474.
- (2) Zhu, H.; Wang, Y.; Xiao, J.; Liu, M.; Xiong, S.; Wong, Z. J.; Ye, Z.; Ye, Y.; Yin, X.; Zhang, X. Observation of Piezoelectricity in Free-Standing Monolayer MoS₂. Nat Nano **2015**, 10, 151–155.
- (3) Fei, R.; Li, W.; Li, J.; Yang, L. Giant Piezoelectricity of Monolayer Group IV Monochalcogenides: SnSe, SnS, GeSe, and GeS. Appl. Phys. Lett. 2015, 107, 173104– 173108.
- (4) Ong, M. T.; Reed, E. J. Engineered Piezoelectricity in Graphene. ACS Nano 2012, 6, 1387–1394.
- (5) Kaul, A. B.; Wong, E. W.; Epp, L.; Hunt, B. D. Electromechanical Carbon Nanotube Switches for High-Frequency Applications. *Nano Lett.* **2006**, *6*, 942–947.
- (6) Zhang, C.; Chen, W.; Zhang, C. Twodimensional Theory of Piezoelectric Plates Considering Surface Effect. *Eur. J. Mech. A-Solid* **2013**, *41*, 50 – 57.
- (7) Kim, K.-H.; Kumar, B.; Lee, K. Y.; Park, H.-K.; Lee, J.-H.; Lee, H. H.; Jun, H.; Lee, D.; Kim, S.-W. Piezoelectric two-dimensional nanosheets/anionic layer heterojunction for efficient direct current power generation. *Sci. Rep.* **2013**, *3*, 2017 EP –.
- (8) Lanza, M.; Reguant, M.; Zou, G.; Lv, P.;Li, H.; Chin, R.; Liang, H.; Yu, D.;

Zhang, Y.; Liu, Z. et al. High-Performance Piezoelectric Nanogenerators Using Two-Dimensional Flexible Top Electrodes. *Adv. Mater. Interf.* **2014**, *1*, 1300101.

- (9) Duerloo, K. A. N.; Ong, M. T.; Reed, E. J. Intrinsic Piezoelectricity in Two-Dimensional Materials. J. Phys. Chem. Lett. 2012, 3, 2871–2876.
- (10) Michel, K. H.; Verberck, B. Theory of Elastic and Piezoelectric Effects in Two-Dimensional Hexagonal Boron Nitride. *Phys. Rev. B* 2009, *80*, 224301.
- (11) Michel, K. H.; Verberck, B. Phonon Dispersions and Piezoelectricity in Bulk and Multilayers of Hexagonal Boron Nitride. *Phys. Rev. B* 2011, *83*, 115328.
- (12) Michel, K. H.; Verberck, B. Theory of Phonon Dispersions and Piezoelectricity in Multilayers of Hexagonal Boron-Nitride. *Phys. Status Solidi B* **2011**, *248*, 2720.
- (13) Zhuang, H. L.; Johannes, M. D.; Blonsky, M. N.; Hennig, R. G. Computational Prediction and Characterization of Single-Layer CrS₂. Appl. Phys. Lett. **2014**, 104, 022116–022119.
- (14) Alyörük, M. M.; Aierken, Y.; Çakır, D.; Peeters, F. M.; Sevik, C. Promising Piezoelectric Performance of Single Layer Transition-Metal Dichalcogenides and Dioxides. J. Phy. Chem. C 2015, 119, 23231–23237.
- (15) Blonsky, M. N.; Zhuang, H. L.; Singh, A. K.; Hennig, R. G. Ab Initio Prediction of Piezoelectricity in Two-Dimensional Materials. ACS Nano 2015, 9, 9885–9891.
- (16) Li, W.; Li, J. Piezoelectricity in Two-Dimensional Group-III Monochalcogenides. Nano Research 2015, 1–7.
- (17) Gomes, L. C.; Carvalho, A.; Castro Neto, A. H. Enhanced Piezoelectricity and Modified Dielectric Screening of

Two-Dimensional Group-IV Monochalcogenides. *Phys. Rev. B* **2015**, *92*, 214103.

- (18) Behmann, R. Elastic and Piezoelectric Constants of alpha-Quartz. *Phys. Rev.* 1958, 110, 1060–1061.
- (19) Lueng, C. M.; Chan, H. L. W.; Surya, C.; Choy, C. L. Piezoelectric Coefficient of Aluminum Nitride and Gallium Nitride. J. Appl. Phys. 2000, 88, 5360–5363.
- (20) Zheng, H.; Li, X.-B.; Chen, N.-K.; Xie, S.-Y.; Tian, W. Q.; Chen, Y.; Xia, H.; Zhang, S. B.; Sun, H.-B. Monolayer II-VI Semiconductors: A First-Principles Prediction. *Phys. Rev. B* **2015**, *92*, 115307.
- (21) Kresse, G.; Hafner, J. Ab Initio Molecular Dynamics for Liquid Metals. *Phys. Rev. B* 1993, 47, 558–561.
- (22) Wu, X.; Vanderbilt, D.; Hamann, D. R. Systematic Treatment of Displacements, Strains, And Electric Fields in Density-Functional Perturbation Theory. *Phys. Rev. B* **2005**, *72*, 035105–035117.
- (23) Perdew, J. P.; Burke, K.; Ernzerhof, M. Generalized Gradient Approximation Made Simple. *Phys. Rev. Lett.* **1996**, 77, 3865–3868.
- (24) Perdew, J. P.; Burke, K.; Ernzerhof, M. Generalized Gradient Approximation Made Simple. *Phys. Rev. Lett.* **1996**, 77, 3865–3868.
- (25) Monkhorst, H. J.; Pack, J. D. Special Points for Brillouin-Zone Integrations. *Phys. Rev. B* 1976, 13, 5188–5192.
- (26) Nunes, R. W.; Gonze, X. Berry-Phase Treatment of the Homogeneous Electric Field Perturbation in Insulators. *Phys. Rev. B* 2001, 63, 155107.
- (27) Çakır, D.; Peeters, F. M.; Sevik, C. Mechanical and Thermal Properties of *h*-MX₂ Monolayers a Comparative Study. *Appl. Phys. Lett.* **2014**, *104*, 203110– 203113.

- (28) Born, M.; Huang, K. Dynamical Theory of Crystal Lattices; Oxford University Press: Oxford, 1988.
 - (29) Nye, J. F. Physical Properties of Crystals, Their Representation by Tensors and Matrices; Clarendon Press: Oxford, 1957.
- (30) Schwerdtfeger, P. Table of Experimental and Calculated Static Dipole Polarizabilities for the Electronic Ground States of the Neutral Elements (in Atomic Units): http://ctcp.massey.ac.nz/Tablepol2015.pdf. **2015**, $\alpha_{\mathbf{Be}}=37.71$, $\alpha_{\mathbf{Mg}}=70.89$, $\alpha_{\mathbf{Ca}}=155.90$, $\alpha_{\mathbf{Sr}}=197.20$, $\alpha_{\mathbf{Ba}}=275.68$, $\alpha_{\mathbf{Zn}}=38.80$, $\alpha_{\mathbf{Cd}}=46.60$, $\alpha_{\mathbf{S}}=19.60$, $\alpha_{\mathbf{Se}}=26.24$, $\alpha_{\mathbf{Te}}=37.00$.

ACS Paragon Plus Environment

Page 10 of 10

Graphical TOC Entry



