

“Germanium vacancy centre formation in CVD nanocrystalline diamond using a solid dopant source”. Mary Joy R, Pobedinskas P, Bourgeois E, Chakraborty T, Görlitz J, Herrmann D, Noël C, Heupel J, Jannis D, Gauquelin N, D'Haen J, Verbeeck J, Popov C, Houssiau L, Becher C, Nesládek M, Haenen K, Science talks 5, 100157 (2023).
<http://doi.org/10.1016/j.sctalk.2023.100157>